

**DICALITE® PERLITE AGENTS**

**DATA SHEET Nr. 06G: Dicalite GPE 108**

**SPECIFICATIONS:**

MINERALOGICAL .....	Perlite: Amorphous Silicate
Physical Form .....	Dry powder
Particle Shape .....	Multihedral Plates
Color .....	White to Off-white
Cake Permeability .....	70 - 120
Wet density .....	12.5 - 15.2 lbs/ft <sup>3</sup>
Float .....	max. 12 (ml/20g)

**TYPICAL SCREEN ANALYSIS:**

Retained on 140 U.S. Mesh screen (0.105 mm): 4 - 8 % (wet screening)  
 Retained on 325 U.S. Mesh screen (0.044 mm): 10 - 35 % (wet screening)

**INHERENT PROPERTIES (NOT PART OF THE PRODUCT SPECIFICATIONS):**

Moisture Content .....	Lower than 1,7 g%
pH .....	min. 5.0 - max. 9.0
Softening point .....	900 °C - 1100 °C
Density .....	
Alfa quarts content .....	Lower than 1,0 %

**OTHER INFORMATION:**

Shipping point .....	Dicalite Europe Ghent
Packaging .....	Dicalite paper bags

FOR FURTHER INFORMATION PLEASE CONTACT YOUR LOCAL DICALITE SALES DISTRICT OR OUR TECHNICAL SERVICE REPRESENTATIVE AT TEL. +32-9-250.95.50.

Specification Nr.: Q01/A/10G Page: 1/1	Date: 11-01-1994 Revised: 3 Updated: 29/02/96	Written by: R. Ysewyn	Reviewed by: Tim Neyt
---	--	-----------------------	-----------------------