

DICALITE® PERLITE AGENTS

DATA SHEET Nr. 00G: Dicalite GPE 08

SPECIFICATIONS:

MINERALOGICAL	Perlite: Amorphous Silicate
Physical Form	Dry powder
Particle Shape	Multihedral Plates
Color	White to Off-white
Cake Permeability	max. 20
Wet density	min. 21.1 lbs/ft ³
Float	max. traces

TYPICAL SCREEN ANALYSIS:

Retained on 140 U.S. Mesh screen (0.105 mm):	0 - 1 % (wet screening)
Retained on 325 U.S. Mesh screen (0.044 mm):	2 - 5 % (wet screening)

INHERENT PROPERTIES (NOT PART OF THE PRODUCT SPECIFICATIONS):

Moisture Content	Lower than 1,7 g%
pH	min. 5.0 - max. 9.0
Softening point	900 °C - 1100 °C
Density	
Alfa quarts content	Lower than 1,0 %

OTHER INFORMATION:

Shipping point	Dicalite Europe Ghent
Packaging	Dicalite paper bags

FOR FURTHER INFORMATION PLEASE CONTACT YOUR LOCAL DICALITE SALES DISTRICT OR
OUR TECHNICAL SERVICE REPRESENTATIVE AT TEL. +32-9-250.95.50.

Specification Nr.: Q01/A/04G
Page: 1/1

Date: 11-01-1994
Revised: 2 Updated: 20/12/94

Written by: R. Ysewyn

Reviewed by: Tim Neyt