

**DICALITE® PERLITE AGENTS**

**DATA SHEET Nr. 01G: Dicalite GPE 18**

**SPECIFICATIONS:**

MINERALOGICAL .....	Perlite: Amorphous Silicate
Physical Form .....	Dry powder
Particle Shape .....	Multihedral Plates
Color .....	White to Off-white
Cake Permeability .....	20 - 45
Wet density .....	max. 26.0 lbs/ft <sup>3</sup>
Float .....	max. 2 (ml/20g)

**TYPICAL SCREEN ANALYSIS:**

Retained on 140 U.S. Mesh screen (0.105 mm):      0 - 1 % (wet screening)  
 Retained on 325 U.S. Mesh screen (0.044 mm):      1 - 15 % (wet screening)

**INHERENT PROPERTIES (NOT PART OF THE PRODUCT SPECIFICATIONS):**

Moisture Content .....	Lower than 1,7 g%
pH .....	min. 5.0 - max. 9.0
Softening point .....	900 °C - 1100 °C
Density .....	
Alfa quarts content .....	Lower than 1,0 %

**OTHER INFORMATION:**

Shipping point .....	Dicalite Europe Ghent
Packaging .....	Dicalite paper bags

FOR FURTHER INFORMATION PLEASE CONTACT YOUR LOCAL DICALITE SALES DISTRICT OR OUR TECHNICAL SERVICE REPRESENTATIVE AT TEL. +32-9-250.95.50

Specification Nr.: Q01/A/05G Page: 1/1	Date: 26-04-2017 Revised: 3    Updated: 21/09/11	Written by: SHEQ-Mgr.	Reviewed by: SHEQ-Mgr.
---	---	-----------------------	------------------------